

FIBROPROTEX PRIMER

One component primer

Description

One-component product with low viscosity based on acrylic colloidal dispersion with fine dimension (0,02-0,04 micron). This product in mineral substrate has high penetration power. Fibroprotex primer contain anti-vegetative additive

Use

Consolidate eternit sheet
Saturate the porosity of SIVITCRETE BASE or SIVITCRETE TOP before the application of top-coating
Primer for wall before the application of CEMENTURA and PITTURA ANTIMUFFA paints.

Treatment of substrate

Apply directly on eternit substrate
On Sivitcem top is possible to apply directly the product diluted with 50% of water.
On eternit remove algae and mould formation after treatment with fibroprotex primer.
In the case eternit surface were rich of algae and moulds would be necessary to treat the surface with fibroprotex risan



Application

On eternit fibroprotex primer must be applied by spray low pressure.
On Sivitcem top apply by roller or brush
The consumption depends on the porosity of the substrate in the case of eternity could pass from 0,150 kg/m² until 0,450 kg/m²
On Sivitcem the consumption is round about 0,100 kg/m² for coat.

Thecnical Data

Color	Translucent	
Aspect	Liquid	
Specific Weight at 25° C	1,00-1,05 g/ml	
Solid content	15% in weight	
Viscosity at 25°C	10-20 mPascal (Spindle 1, rpm 200)	
Tack free time	at 25°C and 50% U.R.	60-70 minuts
	at 28°C and 50% U.R.	35-55 minuts
	at 5° C and 50% U.R.	85-105 minuts
VOC	20 g/l	
Consumption	0,15-0,45 lt/mq, depending on the porosity of the substrate	
Flash point	Not applicable	
Overcoat time	at 23°C and 50% U.R.	4 hours
Application conditions	Temperatures between 5°C ed i 35°C and U.R. < 80%	
Solvent to clean the tools	water	
Dangerous symbols on the labe	None	
Storage	12 months. Keep it in a dry place at a temperature between 5°C ed i 35°C	